AMENDMENTS TO THE CLAIMS

Please enter the following amendments.

Claims 1-5 (Cancelled)

6. (Currently Amended) A method of manufacturing a silicon wafer, comprising the steps of:

~~A)~~ (a) pulling up a single silicon crystal ingot from a silicon melt ~~by controlling V/G; and~~

~~B)~~ (b) slicing said ingot into a silicon wafer; and

(c) heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein said pulling-up of said ingot at the step (a) is carried out ~~is pulled up~~ such that V/Ga and V/Gb become 0.23 to 0.50 mm^2/minute °C, respectively, ~~where V (mm/minute) is a pulling-up speed, and~~ both of V/Ga and V/Gb exceeding a first critical ratio ((V/G)$_1$) for restricting vacancy agglomerates to a vacancy point defect dominant domain at the center of said ingot;

where Ga (°C/mm) is an axial temperature gradient at the center of said ingot and Gb (°C/mm) is an axial temperature gradient at the edge of said ingot at temperatures in a range of 1,300°C to a melting point of silicon;

wherein said heat treatment of said silicon wafer at step (c) is carried out in a 100% hydrogen atmosphere, a mixed atmosphere of hydrogen and nitrogen at temperatures in a range of 1,050°C to 1,220°C for 30 to 150 minutes;

resulting in that the number of crystal originated particles smaller than 0.12 μm in the wafer surface is restricted to a range of 3 to 10 pieces/cm^2; and the number of crystal originated particles of 0.12 μm or greater in the wafer surface becomes 0.5 pieces/cm^2 or less.

Claims 7-22 (Cancelled)

23. (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a) pulling up a single silicon crystal ingot from silicon melt by controlling V/G;

(b) slicing said ingot into a silicon wafer; and

(c) heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a second critical ratio ($(V/G)_2$) for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a third critical ratio ($(V/G)_3$) for restricting agglomerates of vacancy point defects within a center domain dominated by vacancy point defects;

wherein said sliced silicon at the step (b) wafer includes no crystal originated particles nor dislocation pits in the surface of said silicon wafer, and is a silicon wafer in which oxidation induced stacking faults actualize only in a disk shape at the center of said silicon wafer unlike the ring shape, when said silicon wafer was heat treated in an oxygen atmosphere at temperatures of 1,000°C±30°C for 2 to 5 hours and subsequently heat treated at temperatures of 1,130°C±30°C for 1 to 16 hours;

wherein said heat treatment of said silicon wafer at the step of (c) is carried out in an atmosphere of 100% oxygen or in a mixed atmosphere of oxygen and nitrogen at temperatures of 1,130°C to 1,200°C for 1 minute to 6 hours; resulting in obtaining a silicon wafer which is free of crystal originated particles and of oxidation induced stacking faults, when said silicon wafer was heat treated by said oxidation-induced-stacking-fault-actualizing heat treatment.

24. (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a) pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b) slicing said ingot into a silicon wafer; and

(c) heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

-4-

wherein V/G at the step (a) is held at a value which is: equal, to or greater than a second critical ratio $((V/G)_2)$ for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a third critical ratio $((V/G)_3)$ for restricting agglomerates of vacancy point defects within a center domain dominated by vacancy point defects;

wherein said sliced silicon wafer at the step (b) includes no crystal originated particles nor dislocation pits in the surface of said silicon wafer, and is a silicon wafer in which oxidation induced stacking faults actualize only in a disk shape at the center of said silicon wafer unlike the ring shape, when said silicon wafer was heat treated in a oxygen atmosphere at temperatures of 1,000°C±30°C for 2 to 5 hours and subsequently heat treated at temperatures of 1,130°C±30°C for 1 to 16 hours;

wherein said heat treatment of said silicon wafer at the step (c) is carried out in an atmosphere of 100% argon at temperatures of 1,130°C to 1,200°C for 1 minute to 6 hours; resulting in obtaining a silicon wafer which is free of crystal originated particles and of oxidation induced stacking faults, when said silicon wafer was heat treated by said oxidation-induced-stacking-fault-actualizing heat treatment.

25.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b)   slicing said ingot into a silicon wafer; and

(c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a second critical ratio $((V/G)_2)$ for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a third critical ratio $((V/G)_3)$ for restricting agglomerates of vacancy point defects within a center domain dominated by vacancy point defects;

wherein said sliced silicon wafer at the step (b) includes no crystal originated particles nor dislocation pits in the surface of said silicon wafer, and is a silicon wafer in which oxidation induced stacking faults actualize only in a disk shape at the center of said silicon wafer unlike the ring shape, when said silicon wafer was heat treated in a oxygen atmosphere at

temperatures of $1,000°C\pm30°C$ for 2 to 5 hours and subsequently heat treated at temperatures of $1,130°C\pm30°C$ for 1 to 16 hours;

wherein said heat treatment of said silicon wafer at the step (c) is carried out in an atmosphere of 100% hydrogen or in a mixed atmosphere of hydrogen and argon at temperatures of $1,150°C$ to $1,250°C$ for 1 minute to 4 hours; resulting in providing a silicon wafer which is free of crystal originated particles and of oxidation induced stacking faults, when said silicon wafer was heat treated by said oxidation-induced-stacking-fault-actualizing heat treatment.

26.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b)   slicing said ingot into a silicon wafer; and

(c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held in the range from a fifth critical ratio $((V/G)_5)$ to a sixth critical ratio $((V/G)_6)$, the range corresponding to the domain [OSF] for forming OSF nuclei;

wherein said sliced silicon wafer at the step (b) includes no crystal originated particles nor dislocation pits in the surface of said silicon wafer, and is a silicon wafer in which oxidation induced stacking faults are generated only in a disk shape at the center of said silicon wafer, unlike the ring shape, in 25% or more of the entire area of said silicon wafer and oxygen precipitations accompanied with no dislocation generation is generated at a density of 1×10^5 to 3×10^7 pieces/cm^2, when said silicon wafer was heat treated in an oxygen atmosphere at temperatures of $1,000°C\pm30°C$ for 2 to 5 hours and subsequently heat treated at temperatures of $1,130°C\pm30°C$ for 1 to 16 hours;

wherein said heat treatment of said silicon wafer at the step (c) is carried out in a hydrogen gas atmosphere or in an atmosphere including hydrogen gas from a room temperature up to $1,100°C$ to $1,250°C$ at a temperature elevating speed of 3 °C/minute to 150 °C/second;

wherein said heat-treated silicon wafer is held for 1 minute to 2 hours followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 100 μm from the wafer surface, to thereby provide said silicon wafer having a

BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.

    27.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

    (a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

    (b)   slicing said ingot into a silicon wafer; and

    (c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a fourth critical ratio ((V/G)$_4$) for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a fifth critical ratio ((V/G)$_5$) for restricting agglomerates of vacancy point defects to the ingot center domain dominated by vacancy point defects;

wherein said sliced silicon wafer at the step (b) comprises a mixed domain of [P$_V$] and [P$_I$] and has an oxygen concentration of 0.8×10^{18} to 1.4×10^{18} atoms/cm^3 (old ASTM) ,

where [P$_I$] is a domain neighboring with a domain [I] dominated by interstitial silicon point defects, is classified into a perfect domain [P] including no agglomerates of point defects, and has a concentration of interstitial silicons lower than the lowest concentration of interstitial silicons capable of forming interstitial dislocations, and

where [P$_V$] is a domain neighboring with a domain [V] dominated by vacancy point defects, is classified into said perfect domain [P], and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of:

conducting a first step heat treatment for holding said silicon wafer in an atmosphere of nitrogen, hydrogen, oxygen, mixture of nitrogen and argon, mixture of hydrogen and argon or a mixture of oxygen and argon at temperatures of 600°C to 850°C for 120 to 250 minutes; and

subsequently conducting a second step heat treatment for rapidly heating said silicon wafer in a hydrogen gas or in an atmosphere including a hydrogen gas from a room

temperature up to temperatures of 1,100°C to 1,250°C at a temperature elevating speed of 3 °C/minute to 150 °C/second, and for holding said silicon wafer for 1 minute to 2 hours followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 100 μm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.

        28.   (New) A method of manufacturing a silicon wafer comprising the steps of:

        (a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

        (b)   slicing said ingot into a silicon wafer; and

        (c)   heat treating said silicon wafer;

        where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

        wherein V/G at the stop (a) is held at a value which is: equal to or greater than a fourth critical ratio ($(V/G)_4$) for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a fifth critical ratio ($(V/G)_5$) for restricting agglomerates of vacancy point defects to the ingot center domain dominated by vacancy point defects;

        wherein said sliced silicon wafer at the step (b) comprises one or both of a domain $[P_V]$ and a domain $[P_I]$ and has an oxygen concentration of 1.2×10^{18} atoms/cm^3 or more (old ASTM),

        where, in said single silicon crystal ingot,

        said domain $[P_I]$ is a domain neighboring with a domain $[I]$, is classified into a perfect domain $[P]$, and has a concentration of interstitial silicons lower than the lowest concentration of interstitial silicons capable of forming interstitial dislocations,

        said domain $[P_V]$ is a domain neighboring with a domain $[V]$, is classified into said perfect domain $[P]$, and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

        said domain $[I]$ is a domain dominated by interstitial silicon point defects,

        said domain $[V]$ is a domain dominated by vacancy point defects, and

said perfect domain [P] includes no agglomerates of interstitial silicon point defects and no agglomerates of vacancy point defects;

wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of: heating said silicon wafer in an atmosphere of a hydrogen gas or an argon gas from a room temperature up to temperatures of 900°c to 1, 200°C at a temperature elevating speed of 5 to 50 °C/minute; and

holding said silicon wafer for 5 to 120 minutes, to thereby conduct a first step heat treatment followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 5 µm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.

29.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b)   slicing said ingot into a silicon wafer; and

(c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a critical point; and equal to or less than a fifth critical ratio ($(V/G)_5$) for restricting agglomerates of vacancy point defects to the ingot center domain dominated by vacancy point defects;

wherein said sliced silicon wafer at the step (b) comprises a domain [P$_V$] and has an oxygen concentration of 1.2×10^{18} atoms/cm^3 or more (old ASTM),

where, in said single silicon crystal ingot,

said domain [P$_V$] is a domain neighboring with a domain [V], is classified into a perfect domain [P], and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

said domain [V] is a domain dominated by vacancy point defects, and

said perfect domain [P] includes no agglomerates of interstitial silicon point defects and no agglomerates of vacancy point defects;

wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of:

heating said silicon wafer in an atmosphere of a hydrogen gas or an argon gas from a room temperature up to temperatures of 900°C to 1,200°C at a temperature elevating speed of 5 to 50 °C/minute;

holding said silicon wafer for 5 to 120 minutes, to thereby conduct a first step heat treatment;

introducing said silicon wafer in a nitrogen atmosphere or in an oxidative atmosphere from a room temperature into a furnace at temperatures of 500°C to 800°C;

heating said silicon wafer up to temperatures of 750°C to 1,100°C at a temperature elevating speed of 10 to 50 °C/minute; and

holding said silicon wafer for 4 to 48 hours, to thereby conduct a second step heat treatment followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 5 μm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.

30.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b)   slicing said ingot into a silicon wafer; and

(c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a fourth critical ratio (($V/G)_4$) for avoiding occurrence of agglomerates of interstitial silicon point defects; and equal to or less than a critical point; or V/G is held at a value which is: equal to or greater than said fourth critical ratio (($V/G)_4$); and equal to or less than a fifth critical ratio (($V/G)_5$) for restricting agglomerates of vacancy point defects to the ingot center domain dominated by vacancy point defects;

wherein said sliced silicon wafer at the step (b) comprises a domain [P$_I$] or comprises a mixed domain including said domain [P$_I$] and a domain [P$_V$] and has an oxygen concentration of 1.2×10^{18} atoms/cm^3 or more (old ASTM),

where, in said single silicon crystal ingot,

said domain [P$_I$] is a domain neighboring with a domain [I], is classified into a perfect domain [P], and has a concentration of interstitial silicons lower than the lowest concentration of interstitial silicons capable of forming interstitial dislocations,

said domain [P$_V$] is a domain neighboring with a domain [V], is classified into said perfect domain [P], and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

said domain [I] is a domain dominated by interstitial silicon point defects,

said domain [V] is a domain dominated by vacancy point defects, and

said perfect domain [P] includes no agglomerates of interstitial silicon point defects and no agglomerates of vacancy point defects;

wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of:

heating said silicon wafer in an atmosphere of a hydrogen gas or an argon gas from a room temperature up to temperatures of 900°C to 1,200°C at a temperature elevating speed of 5 to 50 °C/minute;

holding said silicon wafer for 5 to 120 minutes, to thereby conduct a first step heat treatment;

introducing said silicon wafer in a nitrogen atmosphere or in an oxidative atmosphere from a room temperature into a furnace at temperatures of 400°C to 700°C;

heating said silicon wafer up to temperatures of 800 to 1,100°C at a temperature elevating speed of 0.5 to 10 °C/minute; and

holding said silicon wafer for 0.5 to 40 hours, to thereby conduct a second step heat treatment followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 5 μm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3, in a portion deeper than said denuded zone and exhibiting an IG effect.

31.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

(a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

(b)   slicing said ingot into a silicon wafer; and

(c)   heat treating said silicon wafer;

where V (mm/minute) is a pulling-up speed, and (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

wherein V/G at the step (a) is held at a value which is: equal to or greater than a critical point; and equal to or less than a sixth critical ratio ($(V/G)_6$) corresponding to a domain [OSF) for forming OSF nuclei;

wherein said sliced silicon wafer at the step (b) comprises a mixed domain of a domain [OSF] and a domain [P_V], and has an oxygen concentration of 1.2×10^{18} atoms/cm^3 or more (old ASTM),

where, in said single silicon crystal ingot,

said domain [OSF] is classified into a domain [V], and OSF's are to generate in said domain [OSF] when said ingot in a silicon wafer state is subjected to a thermal oxidization treatment,

said domain [P_V] is a domain neighboring with a domain [V], is classified into said perfect domain [P], and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

said domain [V] is a domain dominated by vacancy point defects, and

said perfect domain [P] includes no agglomerates of interstitial silicon point defects and no agglomerates of vacancy point defects;

wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of:

heating said silicon wafer in an atmosphere of a hydrogen gas or an argon gas from a room temperature up to temperatures of 900°C to 1,200°C at a temperature elevating speed of 5 to 50 °C/minute;

holding said silicon wafer for 5 to 120 minutes, to thereby conduct a first step heat treatment followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 5 μm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.

      32.   (New) A method of manufacturing a silicon wafer, comprising the steps of:

      (a)   pulling up a single silicon crystal ingot from a silicon melt by controlling V/G;

      (b)   slicing said ingot into a silicon wafer; and

      (c)   heat treating said silicon wafer;

      where V (mm/minute) is a pulling-up speed, and G (°C/mm) is a temperature gradient at an interface between said ingot and silicon melt;

      wherein V/G at the step (a) is held at a value which is: equal to or greater than a critical point; and equal to or less than a sixth critical ratio ($(V/G)_6$) corresponding to a domain [OSF] for forming OSF nuclei;

      wherein said sliced silicon wafer at the step (b) comprises a mixed domain of a domain [OSF) and a domain [P_V], and has an oxygen concentration of 1.2×10^{18} atoms/cm^3 or more (old ASTM),

      where, in said single silicon crystal ingot,

      said domain [OSF] is classified into a domain [V] and OSF's are to generate in said domain [OSF] when said ingot in a silicon wafer state is subjected to a thermal oxidization treatment,

      said domain [P_V] is a domain neighboring with a domain [V], is classified into said perfect domain [P], and has a concentration of vacancies equal to or lower than a concentration of vacancies capable of forming COP's or FPD's,

      said domain [V] is a domain dominated by vacancy point defects, and

      said perfect domain [P] includes no agglomerates of interstitial silicon point defects and no agglomerates of vacancy point defects;

      wherein said heat treatment of said silicon wafer at the step (c) comprises the steps of:

heating said silicon wafer in an atmosphere of a hydrogen gas or an argon gas from a room temperature up to temperatures of 900°C to 1,200°C at a temperature elevating speed of 5 to 50 °C/minute;

holding said silicon wafer for 5 to 120 minutes, to thereby conduct a first step heat treatment;

introducing said silicon wafer in a nitrogen atmosphere or in an oxidative atmosphere from a room temperature into a furnace at temperatures of 500°C to 800°C;

heating said silicon wafer up to temperatures of 750°C to 1,100°C at a temperature elevating speed of 10 to 50 °C/minute; and

holding said silicon wafer for 4 to 48 hours, to thereby conduct a second step heat treatment followed by leaving said silicon wafer at a room temperature; resulting in that a denuded zone is formed over a depth of 1 to 5 μm from the wafer surface, to thereby provide said silicon wafer having a BMD density of 2×10^4 to 2×10^8 pieces/cm^3 in a portion deeper than said denuded zone and exhibiting an IG effect.